

Resin Properties	Unit	Typical Value	Test Method
Melt Index(21.6)	g/10 min	23	ISO 1133
Melt Index(5)	g/10 min	1.2	ISO 1133
FRR (21.6/5)	-	19	-
Density	g/cm ³	0.954	ISO 1183
Notched Impact @ 23 °C	mJ/mm ²	9	ISO 179/ 1 eA