

Test/Composition	Typical Value	Unit	ASTM Method
Density	0.948	g/ml ³	ISO1183
FRR 21.6/5	28		
Hydrostatic Strength (80°C)	5000 (4.5N/mm ²)	h	ISO1167
MFR190°/21.6	6.2	g/10 min	ISO1133
MFR190°/5	0.22	g/10 min	ISO1133
Notched Impact (23°C)	24	mJ/mm ²	ISO179/1eA