

Resin Properties	Unit	Typical Value	Test Method
Melt Index (2.16)	g/10 min	12	ISO 1133
Melt Index (5)	g/10 min	0.45	ISO 1133
FRR (21.6/5)	-	27	-
Density	g/cm ³	0.945	ISO 1183
Notched Impact @ 23 °C	mJ/mm ²	12	ISO 179/ 1 eA
Hydrostatic Strength (80 °C)	h	(4.0 N/mm ²) 1000	ISO 1167