

Resin Properties	Unit	Typical Value	ASTM Method
Melt Index (190°C/ 2.16Kg)	g/10 min	18	D1238
Density	g/ml	0.952	D1505
Vicat Softening Point	°C	121	D1525
Flexural Modulus	MPa	1200	D790
Notched Izod Impact @ 23 °C	J/m	19	D256/A