

Resin Properties	Unit	Typical Value	Test Method
Melt Index (2.16)	g/10 min	9.5	ISO 1133
Melt Index (5)	g/10 min	0.35	ISO 1133
FRR (21.6/5)		27	
Density	g/cm ³	0.951	ISO 1183
Swell Ration	%	110	
Notched Impact @ 23 °C	mJ/mm ²	10	ISO 179/ 1 eA