

<b>Resin Properties</b>	<b>Unit</b>	<b>Typical Value</b>	<b>Test Method</b>
Melt Index (190°C/ 2.16Kg)	g/10 min	2.1	D1238
Density	g/cm <sup>3</sup>	0.952	D1505
Vicat Softening Point	°C	124	D1525
Flectural Modulus	Mpa	1000	D790
Tensile Strength at Yield	Mpa	25	D790
Tensile Strength at Break	Mpa	38	D638
H.D.T	°C	78	D648
Notched Izod Impact @ 23 °C	J/m	180	D256/A