

Resin Properties	Unit	Typical Value	Test Method
Melt Index (190°C/ 2.16Kg)	g/10 min	1.0	D1238
Density	g/cm ³	0.952	D1505
Vicat Softening Point	°C	123	D1525
Flectural Modulus	Mpa	800	D790
Tensile Strength at Yield	Mpa	25	D790
Tensile Strength at Break	Mpa	36	D638
H.D.T	°C	78	D648
Notched Izod Impact @ 23 °C	J/m	80	D256/A